

Hard thin film coatings deposited by Cathodic Arc Physical Vapor Deposition technique

R.J. Talib^{1,*}, M.F. Fazira², H.M. Ariff³

¹⁾ Faculty of Mechanical Engineering, Universiti Teknologi MARA, 1300 Permatang Pauh, Pulau Pinang, Malaysia.

²⁾ AMREC, SIRIM Bhd, Lot 34, Jalan Hi-Tech 2/3 Kulim Hi-Tech Park, 09000 Kulim, Malaysia.

³⁾ Protection and Biophysical Division, Science and Technology Research Institute of Defence Kompleks Induk STRIDE, Taman Bukit Mewah Fasa 9, 43000 Kajang, Selangor, Malaysia.

*Corresponding e-mail: drtalib@ppinang.uitm.edu.my

Keywords: Hard thin film; critical load; wear mechanism; friction and wear

ABSTRACT – Physical vapor deposition technique is used to deposit hard and wear resistant thin film of coating material into the substrate surface without changing the substrate properties; commonly referred as thin films. Hard thin film coatings are employed to enhance the surface characteristics of the substrates such as hardness, surface roughness, wear resistance and corrosion resistance without changing the bulk properties of the substrates. Demands for transition metal nitrides such as TiCN, TiCrN, TiAlN, CrAlN synthesized by physical vapor deposition (PVD) as hard film coatings are increasing rapidly due to their superior mechanical, tribological, and corrosion characteristics, thus increasing the components life and productivity of the production. These metal nitride coatings are used to improve friction, wear and life of cutting tools, mould and dies, machine elements, automotive components. Type of coating applied on the substrate depends on the applications of that component.

Physical vapor deposition uses physical forces to deposit a pure source material which is gasified via evaporation. Physical vapor deposition is performed at relatively low temperature (300° to 600°C) as compared to chemical vapor deposition operating at a temperature of 1000°C. The stoichiometric composition of the film arises from reactive gas absorption by growing films, reactive collision between gas molecules and vapour species emitted from the evaporation source, and surface reaction between gas molecules and condensed films.

Quality of thin film coating produced on the substrate depends on; (i) surface preparation such as degreasing and polishing, surface pre-cleaning such as ultra-sonic and plasma sputtered etching, (ii), deposition parameters such as substrate temperature, chamber pressure, current, reactive and working gas flow rate, negative bias voltage, and (iii) target shape, geometry of the chamber, and the position of the substrate relative to the target. Though the physical vapor deposition has been used widely and many researches have been conducted, there are some opportunities in developing high quality in hard thin film coating. These include (i) optimizing the coating process parameters using Taguchi or Design expert method, (ii) determining significant effect of coating process parameter on the mechanical and tribological properties, (iii) determining residual stress in thin film coating, (iv)

establishing failure mechanism on different type of coating materials, (v) developing life predicting model.

In this keynote lecture, results of some works in depositing hard thin film of TiN, TiZrN, TiCN, TiAlN on high speed steel and tungsten carbide substrates will be presented and discussed. The tool life and wear mechanism of coated-drill during drilling and coated-cutting tool insert during turning will also be presented and discussed. The characterization tools employed in this study include (i) x-ray photo electron spectroscope, (ii) x-ray diffraction, (iii) pin-on-disc tribometer, (iv) glow discharge optical emission spectroscope, (v) field emission scanning electron microscope, (vi) scratch tester, and (vii) microhardness tester.

REFERENCES

- [1] R.J. Talib, F.F. Zulkifli, M.A. Hamid, A.H. Hashim, Effect of Temperature on TiCrN Films Prepared by Cathodic Arc Physical Vapour Deposition, *Malaysian Journal of Microscopy* (2), 2006. 86-91.
- [2] R.J. Talib, M.R.M. Toff, H.M. Ariff. Wear Mechanism of TiN, TiAlN AND TiCN Coated Drills During Drilling of Medium Carbon Steel. *Physical Science*, Vol 18 (1), 2007. 75-85.
- [3] R.J. Talib, A.H. Hashim, H.M. Ariff, and M.R.M. Toff. AES Analysis and Drilling Performance of TiN-Coated HSS Drill Deposited. *Proc. The 2nd International Conference on Technological Advances Of Thin Films & Surface Coatings*, Singapore 13 Jul 2004 - 17 Jul 2004.
- [4] R.J. Talib, H.M. Ariff and M.F. Fazira. Machining Performance and Wear Mechanism of TiAlN-Coated Insert. *International Journal of Mechanical and Materials Engineering (IJMME)*, Vol.6 No.3, 2011, 414-418
- [5] Siow Ping Chuan, Jaharah A. Ghani, Mariyam Jameelah Ghazali, Talib Ria Jaafar, Mohamad Asri Selamat, Che Hassan Che Haron. Characterization of TiCN and TiCN/ZrN Coatings for Cutting Tool Application. *Ceramics International*, 39, 2013. 1293–1298.
- [6] M.F. Fazira, A.M. Samsiah, M. Amin, M.A. Selamat, R.J. Talib, Optimization of TiAlN Coatings on HSS Inserts By Physical Vapour Deposition Process Using Taguchi Technique, *Advanced Materials Research* Vol 879, 2014, 27-31